
DuploMED® 8171

Transparent 50 µm (1.97 mil) transfer tape with pure acrylic adhesive (solvent-based)

Product features

- Suitable as adhesive tape for medical devices
- Good waterproof performance
- Good breathability
- Medical-grade adhesive
- Sterilizable by gamma radiation (25 or 50 kGy) or ethylene oxide (35-55 °C)
- Biocompatibility (according to ISO 10993)

Product construction



Typical application fields

Medical

- Fixation of devices to skin patches of wearables
- Fixation of the outer bag closure system of ostomy bags
- Fixation of the charcoal filter mounting of ostomy bags
- Mounting of monitoring electrodes

Product construction

Component	Description	Color	Thickness (typical value)	
Liner	Siliconized paper	white	78 µm	3.07 mil
Adhesive	Pure acrylic	transparent	∑ 50 µm	∑ 1.97 mil

DuploMED® 8171

Transparent 50 µm (1.97 mil) transfer tape with pure acrylic adhesive (solvent-based)

Performance profile - Standard test data

Data show representative values and are not regularly observed by internal quality control. They are not permitted to be used for specification purposes.

Product property	Substrate	Representative value		According to	Test conditions
Peel adhesion (closed side) 	stainless steel	5 N/cm	46 oz/in	DIN EN ISO 29862	Dwell time: 1 day Temperature: 23 °C (73.4 °F) Test angle: 180 ° Tape width: 25 mm Test speed: 300 mm/min
	PE	4 N/cm	37 oz/in		
Tensile shear strength 	stainless steel / stainless steel		400 kPa	AFERA 4029	Dwell time: 2 days Temperature: 23 °C (73.4 °F) Test speed: 12.7 mm/min Bonding area: 625 mm²
Liner release 		0,5 N/cm	5 oz/in	DIN EN ISO 29862	Test angle: 180 ° Tape width: 25 mm Test speed: 300 mm/min Test temperature: 23 °C

DuploMED® 8171

Transparent 50 µm (1.97 mil) transfer tape with pure acrylic adhesive (solvent-based)

Storage and shelf life

The shelf life of DuploMED® 8171 is 2 years after delivery. The duration indicated requires storage in original packaging at 15.0 °C to 30.0 °C (59 °F to 86 °F), normal humidity (30-70 % RH) and absence of UV radiation.

Delivery forms

DuploMED® 8171 is produced as log roll in a usable width of 1,260 mm (49.61 in). It can be converted in different delivery forms upon request:



Roll



Diecut

Service temperature

We recommend the use of DuploMED® 8171 in a range from 18 °C (64.4 °F) to 40 °C (104 °F). The temperature resistance depends on the loads and external influences on the adhesive bond.

Customized production technologies

From adhesive development to automation-ready solutions – Lohmann offers high-tech bonding processes from a single source. Our integrated value chain ensures efficiency, flexibility and reliable quality across every step: coating, laminating, converting, precision die-cutting and more. We support you not only with custom die-cuts, rolls, spools or sheets in various formats, but also with application tools and detailed engineering for seamless process integration – whether manual, semi-automatic or fully automated. Discover our full value chain: https://lohmann-tapes.com/production-technologies

Use instructions

For general information about the handling of pressure sensitive adhesive tapes, please go to https://lohmann-tapes.com/general-usage-instruction

DuploMED® 8171

Transparent 50 µm (1.97 mil) transfer tape with pure acrylic adhesive (solvent-based)

Biocompatibility

Customers should perform their own assessment to ensure the final product is in compliance with all applicable Medical Device regulatory requirements. To support the assessment, and upon request, Lohmann can provide, where available, biocompatibility testing results (ISO10993) specific to either the product supplied by Lohmann or its' constituent components.

Responsible solutions in every bond

For more information on our path to a sustainable vision, please go to: https://lohmann-tapes.com/sustainability

Disclaimer

The physical characteristics contained in this data sheet represent typical or average values. They explicitly do not constitute product specifications. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. Many factors beyond our control and uniquely within buyer's knowledge and control can affect the use and performance of our tape in a particular application. Except as expressively agreed in writing we do not take over any warranty or liability for the suitability or usability of our tapes for certain purposes and applications resulting from buyer's special usage of the tapes. Except where provided by mandatory legal provisions, we will not be liable for any direct or indirect material or immaterial losses or damages arising from the usage or application of our tapes. Solely the buyer is responsible for determining the suitability of the specific tape for its use in connection with his method of application. We refer to DIN EN ISO 21368:2024-10. Please consult our Technical Applications Department for specific advice.

Lohmann GmbH & Co. KG
Irlicher Strasse 55
56567 Neuwied
Germany

For further information
www.lohmann-tapes.com